

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 12.6.2023 Printed 28.3.2024

WINTER-TIME MASONRY MORTAR TML



Product description

Fescon Winter-time Masonry Mortar is a masonry cement based dry mortar for winter-time masonry in the temperature range -15°C...+5°C. The maximum grain size is 3.0 mm.

- Easy to use
- Good workability characteristics

Applications

- Winter-time masonry with lightweight aggregate and concrete blocks, and burnt bricks

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

Instructions

Mixing

Refer to the bag for how much water the plaster requires. Add the dry material to cold water and mix with a concrete mixer for around ten minutes. With a power mixer or a drill paddle, around two to three minutes of mixing is sufficient. Let the plaster stand for around five minutes and mix it again for a short while. Find the correct consistency at this stage by gradually adding the rest of the water. We do not recommend adding all of the water right at the start. The finished plaster remains workable for around 30 minutes to one hour.

Work instructions

Block Mortar Winter is designed for masonry in the temperature range -15°C...+5°C. Follow the instructions of the designers and official regulations in masonry work. National Building Code of Finland B8, Brick Structures. Instructions 2007. SFS handbook 176.

Other points to note

Winter products will be available in the winter season, from 15 September to 1 March. At other times, the products must be ordered separately.

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>



Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 12.6.2023 Printed 28.3.2024

Technical information

Material usage	approx. 4 kg / H75 - UH150 approx. 7 kg / UH200 - RUH380
Water requirement	2.5 - 3.0 l / 25 kg
Finished compound	13 - 14 l / 25 kg bag
Type	powder
Colour	gray
Maximum grain size	3 mm
Package size	25 kg
Storage	storage time in a dry location approx. 1 year
Usage temperature	-15°C...+5°C
Workability time	0.5 - 1 h
Compressive strength	M 10
Adhesion strength	$\geq 0,16 \text{ N/mm}^2$ (SFS-EN 998-2, 5.4.2 a)
Reaction to fire	A1
Heat conductivity	0,72 [w/(m•K)], P=50%
Chloride content	< 0.01 %
Water vapour permeability	μ 15/35
Water absorption by capillarity	0,15 kg/(m ² · min ^{0,5}) (EN1015-18)