

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 26.3.2024 Printed 29.3.2024

TILE ADHESIVE PLASTER VSL



Product description

Fescon Tile Adhesive Plaster VSL is an M1-rated dry mortar with a cement binder. Enables tiling without strips or other spacers, see research report VTT-S-03707-10. A frost-resistant adhesive plaster, see test report VTT-S-05960-12. Suitable for indoor and outdoor use.

- Easy to use
- Good workability characteristics
- Good adhesion strength ($> 2 \text{ N/mm}^2$)
- Meets the C2 tensile strength requirements
- S1 flexibility class
- Non-sag (T)
- For floors with underfloor heating

Applications

- Suitable for dry and humid walls and floors with concrete, tile, plastic and painted surfaces, and surfaces coated with Fescon Waterproofing Compound both indoors and outdoors, and floors with underfloor heating.

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

Instructions

Base

- Clean, undamaged, dust-free and level
- If you are laying tiles on top of an old coating, you must ensure the adhesion of the old coating and roughen the base.
- Sufficient strength and load-bearing capacity
- Switch underfloor heating off two days before tiling
- The relative humidity of the underfloor structure is less than 90% RH
- Temperature $> +10^\circ\text{C}$
- Loose coatings, cement paste and other impurities must be mechanically removed

Instructions for use

- Mix a bag (20 kg) of the levelling compound in around 6.0 litres of cold water
- mix into a consistent mass with a power mixer or a drill paddle.
- spread the plaster on the base while pressing hard and rake it.
- Workable for about three hours after adding water
- Wash tools with water immediately after completing the work
- Remove dried plaster mechanically



Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

- Choose the tooth size of the plastering trowel according to the size of the tile and the adhesion surface.

Grouting

- Grout after around one day with absorbent bases with solid bases and waterproofed surfaces, grout after 2-5 days.

Other considerations

- The information is based on tests and practical experience. We cannot affect conditions at the work site so we cannot assume responsibility for the end result affected by local conditions.

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Material usage	2-4 kg/m ² depending on the base and the tile
Water requirement	max. 6 l/20 kg
Binder	special cement and polymer compound
Colour	gray
Maximum grain size	0.6 mm
Package size	5 kg and 20 kg
Storage	1 year in a dry locatio
Usage temperature	+10°C...+25°C
Workability time	approx. 3 h
Open time	approx. 15 min
Groutable	1-5 days