

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 4.8.2023 Printed 29.3.2024

PRIMER PLUS



Product description

Fescon Primer PLUS is a water-soluble, synthetic rubber latex with additives improving adhesion. The product is designed for the priming of non-absorbent surfaces before levelling. Not suitable for use together with solvent-based adhesives. For indoor use.

- Ready for use
- For the priming of non-absorbent surfaces
- Drying time about 1 h

Applications

- Natural stones
- Film faced plywood
- Ceramic and glass surfaces
- Steel surfaces
- Quartz vinyl tiles and other such hard floor materials
- For priming Gypsum plaster mix GL on hard and non-absorbent precast concrete surfaces

Instructions

Pretreatment of the base

- The base must be sufficiently strong and immobile, and have a sufficient load-bearing capacity
- The pull-out strength of the base must be a minimum of 0.5 MPa
- The relative humidity must be below the requirement of the surface material
- Remove dust, dirt, oil, grease and all loose materials from the base
- Protect corrosion-sensitive metal surfaces before priming

Mixture

- The product is ready-to-use

Applying the primer

- The well-mixed primer is applied as a thin, even layer by brushing (avoid puddles).
- The primer must have dried before further work; its drying time around 1 hour (+15°C / 50% RH).
- Wash tools and equipment with water immediately.

Other considerations

- Not suitable for use together with solvent-based adhesives



Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 4.8.2023 Printed 29.3.2024

Technical information

| | |
|------------------------------|--|
| Material usage | app. 150 g/ m ² (app. 33 m ² / 5kg) |
| Colour | blue |
| Package size | 5 kg |
| Storage | 12 months in a closed container in a cool location, do not allow to freeze |
| Density | 1 l = 1.5 kg |
| Usage temperature | +10°C...+25°C |
| Drying time | app. 1 h (+15°C, RH 50 %) |
| Thinner | water |
| Method of application | brushing |
| Transport | warm transport |