

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 19.3.2026 Printed 26.6.2026

GROUTING CONCRETE TJB WINTER



Product description

Fescon Grouting Concrete Winter is a special concrete that expands before setting. Casting work will succeed in winter at temperatures as low as -15°C.

- Strength class C 40/50 (28 days at -5°C + 28 days at +2°C)
- No chlorides
- Good workability
- Excellent casting properties
- Low drying shrinkage

Applications

- Jointing of prefabricated elements
- Grouting of municipal engineering connections
- Grouting
- Anchor casting

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

Instructions

Base

The base must be undamaged, clean, and damp enough to be darker in colour. Snow and ice must be melted away from the base. If necessary, also remove the weak-strength cement paste layer. Best adhesion can be achieved to a rough base. The mould must be tight, because Fescon Grouting Concrete Winter is pliable and flows easily while it is workable. When using galvanised steels, you must make absolutely sure that the coating has become passive.

Mixing

Refer to the bag for how much water the concrete requires. Add the dry material to the water and mix with a concrete mixer for around three to five minutes. With a power mixer, around two to three minutes of mixing is sufficient. Let the mass stand for a while and mix it again for a short while. Find the correct consistency at this stage by gradually adding the rest of the water. We do not recommend adding all of the water right at the start. If you are unable to use the concrete immediately after mixing, we recommend mixing it again before casting. The finished concrete remains workable for around half an hour. If several bags are mixed at the same time, the heat from the hydration reaction can shorten the workability time. We recommend mixing one or two bags at a time.

Work instructions

Casting should be done as soon as possible after mixing. If necessary, vibrate the casting lightly or ram it. The recommended casting layer thickness is 15-100 mm. Follow the instructions of the



Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

designers and the official regulations on winter concreting when doing casting work.

After treatment

The fresh casting must be protected from snow and rain. You must care for the casting with, for example, a plastic cover or curing compounds. The aftercare should continue for around 7 days. Strength development continues without additional heating in temperatures above -15°C.

Other points to note

Winter products will be available in the winter season, from 15 September to 1 March. At other times, the products must be ordered separately.

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 19.3.2026 Printed 26.6.2026

Technical information

Water requirement	3.5 - 4.0 l/25 kg of dry material
Finished compound	11-12 l/25 kg of dry material
Composition	Portland cement, natural sand (max. grain size 3.0 mm), and additives that make the fresh mass expand, improve workability and ensure strength development in freezing temperatures.
Package size	25 kg and 1000 kg
Storage	Approx. 8 months in a dry location
Usage temperature	-15°C...+5°C
Workability time	Approx. 0.5 h
Plasticity	Approx. 1 sVB
Strength class	C 40/50
Strength development	Strength development with a water amount of 3.8 l/25 kg of dry material (prism strength)
Volume change	< +5 %
Reaction to fire	A1
Exposure class	XC 4, XD 3, XS 3, XF 1, XA 1
Frost resistance	Frost-resistant

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.