

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

## WINTER-TIME MASONRY MORTAR TML



### Product description

Fescon Winter-time Masonry Mortar is a masonry cement based dry mortar for winter-time masonry in the temperature range -15°C...+5°C. The maximum grain size is 3.0 mm.

- Easy to use
- Good workability characteristics

### Applications

- Winter-time masonry with lightweight aggregate and concrete blocks, and burnt bricks

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

### Instructions

### Mixing

Refer to the bag for how much water the plaster requires. Add the dry material to cold water and mix with a concrete mixer for around ten minutes. With a power mixer or a drill paddle, around two to three minutes of mixing is sufficient. Let the plaster stand for around five minutes and mix it again for a short while. Find the correct consistency at this stage by gradually adding the rest of the water. We do not recommend adding all of the water right at the start. The finished plaster remains workable for around 30 minutes to one hour.

### Work instructions

Block Mortar Winter is designed for masonry in the temperature range -15°C...+5°C. Follow the instructions of the designers and official regulations in masonry work. National Building Code of Finland B8, Brick Structures. Instructions 2007. SFS handbook 176.

### Other points to note

Winter products will be available in the winter season, from 15 September to 1 March. At other times, the products must be ordered separately.

### Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>



Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

Updated 29.3.2026 Printed 31.5.2026

## Technical information

<b>Material usage</b>	Approx. 4 kg / H75 - UH150 Approx. 7 kg / UH200 - RUH380
<b>Water requirement</b>	2.5 - 3.0 l / 25 kg
<b>Finished compound</b>	13 - 14 l / 25 kg bag
<b>Type</b>	Powder
<b>Colour</b>	Grey
<b>Maximum grain size</b>	3 mm
<b>Package size</b>	25 kg
<b>Storage</b>	Storage time in a dry location approx. 1 year
<b>Usage temperature</b>	-15°C...+5°C
<b>Workability time</b>	0.5 - 1 h
<b>Compressive strength</b>	M 10
<b>Adhesion strength</b>	≥0,16 N/mm <sup>2</sup> (SFS-EN 998-2, 5.4.2 a)
<b>Reaction to fire</b>	A1
<b>Heat conductivity</b>	0,72 [w/(m•K)], P=50%
<b>Chloride content</b>	< 0.01 %
<b>Water vapour permeability</b>	μ 15/35
<b>Water absorption by capillarity</b>	0,15 kg/(m <sup>2</sup> · min <sup>0,5</sup> ) (EN1015-18)
<b>GWP A1 raw material</b>	0,0828
<b>GWP A2 transport</b>	0,00493
<b>GWP A3 manufacturing</b>	0,0269
<b>GWP A1-A3</b>	0,115
<b>GWP A4 transport</b>	0,0158
<b>GWP A5 assembly</b>	0,00279
<b>GWP unit</b>	kg CO2e/kg

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.