

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

## NANTEN HM W



### Product description

2-component, M1-classified, water vapor permeable, trowel-applied epoxy coating.

- Water-based epoxy resin for trowel-applied coating systems on old and new concrete floors
- Resistant to water, common cleaning agents, salts, and, under temporary exposure, diluted acids and alkalis
- Low-emission

### Applications

- Areas subject to medium-duty wear
- Ground-supported floors

### Instructions

## Base requirements and coating conditions

The concrete strength class must be at least C25/30 with a wear resistance class of 3. The relative humidity of the concrete must be below 98%, and the surface temperature must be at least +3°C above the dew point. During application and curing, the temperature of the air, surface, and coating must remain above +15°C, and the relative humidity of the air must be below 80%.

## New concrete floor

Cement laitance and any uncured cement must be removed by surface grinding or shot blasting. All loose and adhesion-reducing material must be removed, and the surface must be thoroughly vacuumed to remove all cement dust.

## Old concrete floor

Cement laitance and deteriorated concrete must be removed by grinding or shot blasting. All loose and adhesion-reducing material must be removed, and the surface must be thoroughly vacuumed. Dirty floors should be washed and rinsed with a synthetic detergent before any further surface preparation. Any existing old paint film must be completely removed from the substrate.

## Priming

Priming is done by rolling a Nanten HM W mixture thinned with warm water (approx. +30°C). Adhesion sand is broadcast onto the primer film as work progresses, to prepare for subsequent coating. Once the primer has cured, any excess sand is removed by brushing and vacuuming.

## Patching

Small holes and cracks are cleaned and filled with an epoxy putty made of for example, HM W Epoxy and fine filler sand.

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

## Mixing

Pre-mix Part A and Part B of HM W Epoxy in their own containers. Estimate the required amount of mixture based on the size of the area to be treated and the working time of the product. Combine the components in the correct volume ratio and mix thoroughly with a low-speed mechanical mixer for approximately two minutes, avoiding air entrapment in the mixture. Add the required amount of the selected sand blend to the mixture while mixing, and continue until the mixture is uniform, making sure to reach the corners of the mixing container. For priming, add water as the final component after mixing and continue mixing for approximately 2 minutes.

## Mixing ratio

Part A: 1 parts by volume, Part B: 2 part by volume

## Coverage

At 3 mm film thickness

Resin consumption approx. 1.0 l/m<sup>2</sup>

For priming: 0.2–0.3 l/m<sup>2</sup>

For top coating: 0.3–0.35 l/m<sup>2</sup>

Color sand consumption approx. 5 kg/m<sup>2</sup>

## Coating

The mixed material is poured onto the floor in a bead and spread with a notched trowel to the desired thickness. Application is carried out in strips, allowing finishing from untreated areas of the floor. The coating material is compacted with a steel trowel to achieve a smooth surface.

## Top coating

The compacted trowel-applied coating is sealed by rolling on Nanten HM W Epoxy. The topcoat is typically applied in two coats as thin films.

## Coved skirtings

Coved skirtings are made using the same trowel-applied mortar, stiffened with thickening fiber (Sylothix) to facilitate application.

**Note!** Inadequate mixing of the epoxy coating may lead to uneven curing, and an incorrect mixing ratio may result in the coating not curing at all. Do not scrape material from the sides of the container onto the floor.

## Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

## Technical information

<b>Colour</b>	The color of the coating is determined by the selected color sand or color sand blend (Nanten color chart)
<b>Gloss group</b>	Glossy (binder)
<b>Package size</b>	Available in 18-litre sets (6 l + 12 l) or with both components in 200 l drums
<b>Storage</b>	+5°C...+25°C, maximum shelf life 12 months. Store in a warm environment, sealed in original containers.
<b>Mixing time</b>	Approx. two minutes
<b>Density</b>	1.04 kg/l
<b>Usage temperature</b>	+15°C...+25°C
<b>Usage time</b>	Poured onto the floor: approx. 30 minutes. Working time decreases as temperature rises.
<b>Drying time</b>	Touch-dry in 5 h (+25°C) and 9 h (+15°C). Resists light traffic after approx. 12 h (+25°C) and approx. 24 h (+15°C). Fully cured in 7-14 days.
<b>Adhesion strength</b>	1.5 N/mm <sup>2</sup>
<b>Reaction to fire</b>	Bfl-S1
<b>Water vapour permeability</b>	Class I
<b>Relative air humidity</b>	Below 80% during application and curing of the coating
<b>Solids content</b>	Binder approx. 46% by volume
<b>Chemical resistance</b>	Class II
<b>Thinner</b>	For priming, dilute with warm water by approx. 10%. Do not dilute the product when used as a binder in the coating mortar or as a topcoat.
<b>Method of application</b>	Applied with a notched trowel and finished with a steel trowel or mechanically with a power trowel. For priming and top coating, use a suitable roller.
<b>VOC content</b>	< 30 g/l (ready-to-use mixture) EU VOC 2004/42/EC (Cat A/j) max. 140 g/l (2010)
<b>Washing tools</b>	Clean with water or synthetic detergent

Remember to consult the Maintenance Instructions for Coated Floors and the product Safety Data Sheet on our website at [www.fescon.fi](http://www.fescon.fi), or request a copy by calling +358 9 274 7970. Although the technical details provided in this product description are based on our best knowledge and experience, the information above should always be regarded as indicative. The user is responsible for verifying the suitability of the product for the intended application. If the instructions are not followed, the user assumes full responsibility for any resulting damage or consequences.

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
[www.fescon.fi](http://www.fescon.fi)

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.