Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

NANTEN ACRYLIC HARDENER

CE

Product description

Powder-form Acrylic hardener that initiates the curing reaction of acrylic resins.

Applications

• Used as a catalyst for the curing reaction of acrylic resins in all Nanten acrylic coating systems

Instructions

Application instructions

The required amount of Nanten Acrylic Hardener depends on the type of acrylic resin used and the application temperature. The hardener dosage is 1–6% of the amount of acrylic resin used.
1 dl of hardener = 64 g

Waste handling

Storage and handling of waste
See the separate storage and disposal instructions https://www.fescon.fi/en/material-bank

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Material usage	The required amount of Nanten Acrylic Hardener depends on the type of acrylic resin used and the application temperature. The hardener dosage is 1–6% of the amount of acrylic resin used. 1 dl of hardener = 64 g.
Colour	White
Package size	25 kg box
Storage	+5°C...+20°C, maximum storage time 6 months. Store in a warm place, separately from acrylic resins, protected from moisture, and in tightly sealed original containers.
Usage temperature	+3°C...+30°C

Remember to consult the Maintenance Instructions for Coated Floors and the product Safety Data Sheet on our website at www.fescon.fi, or request a copy by calling +358 9 274 7970. Although the technical details provided in this product description are based on our best knowledge and experience, the information above should always be regarded as indicative. The user is responsible for verifying the suitability of the product for the intended application. If the instructions are not followed, the user assumes full responsibility for any resulting damage or consequences. Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.