

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 10.2.2026 Printed 13.5.2026

NANTEN ACRYLIC SEALER 319



Product description

Medium-viscosity, fast-curing, elastic topcoat for Nanten acrylic coating systems.

- Used as a topcoat in acrylic coating systems in areas subject not only to mechanical stress but also to thermal stress caused by hot and cold water
- The topcoat has good UV resistance and, thanks to its elasticity, is also suitable for outdoor use



Applications

- Food and process industry facilities
- Commercial kitchens and laundries
- Outdoor areas
- Loading docks, waste collection shelters, and storage areas

Instructions

Base requirements and coating conditions

The acrylic surface to be coated must be clean and dry. The surface temperature must be at least +3°C above the dew point. Adequate ventilation must be ensured during application. Odours generated during the work can be reduced by using negative pressure ventilation.

Mixing

Pre-mix the required amount of Nanten Acrylic Sealer 319. Assess the effect of temperature on the required amount of hardener and add the hardener to the mixing container. Continue mixing for approximately two minutes.

Mixing ratio

Nanten Acrylic Hardener is used as the hardener, and the required amount depends on the working temperature.

1 dl of hardener = 64 g

+30°C 1 wt-%

+20°C 1.5 wt-%

+10°C 3 wt-%

+3°C 5 wt-%

Coverage

Approx. 0.3–0.5 kg/m², depending on the porosity and roughness of the substrate. A minimum of >0.3 kg/m² per application must be used to ensure proper curing.

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Application instructions

Thoroughly mixed Nanten Acrylic Sealer 319 is poured onto the floor in a bead and applied using a short-nap roller or a rubber squeegee. Once the topcoat has dried, a second coat may be applied if necessary.

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Colour	Colorless. Can be tinted with suitable color pastes or by pigmentation.
Package size	20 kg metal container and 180 kg drum
Storage	+5°C to +25°C, shelf life up to 6 months. Must be stored in a warm location in tightly sealed original containers.
Mixing time	Approx. two minutes
Density	0.98 kg/l, DIN 51757
Usage temperature	+3°C...+30°C
Usage time	Once poured onto the floor: approx. 15 minutes. Working time shortens as temperature increases.
Drying time	Recoat after approx. 60 minutes. Fully loadable after approx. 2 hours.
Adhesion strength	> 2.0 MPa
Tensile strength	MPa
Viscosity	(+25°C): 160-200 mPas
Thinner	Do not dilute
Method of application	Applied with a rubber squeegee or mohair roller
VOC content	< 0 g/l EU VOC 2004/42/EC (Cat A/j) max. 500 g/l (2010)

Remember to consult the Maintenance Instructions for Coated Floors and the product Safety Data Sheet on our website at www.fescon.fi, or request a copy by calling +358 9 274 7970. Although the technical details provided in this product description are based on our best knowledge and experience, the information above should always be regarded as indicative. The user is responsible for verifying the suitability of the product for the intended application. If the instructions are not followed, the user assumes full responsibility for any resulting damage or consequences. Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.