

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 25.4.2025 Printed 20.5.2026

NANTEN ACRYLIC SEALER 305



Product description

Low-viscosity, fast-curing, elastic topcoat for Nanten acrylic coating systems.

Applications

- Used as a topcoat in acrylic coating systems in areas subject to mechanical stress as well as exposure to various chemicals, fats, and similar substances.



Instructions

Base requirements and coating conditions

The acrylic surface to be coated must be clean and dry. The surface temperature must be at least +3°C above the dew point. Adequate ventilation must be ensured during application. Odours generated during the work can be reduced by using negative pressure ventilation.

Mixing

Pre-mix the required amount of Nanten Acrylic Sealer 305. Assess the effect of temperature on the required amount of hardener and add the hardener to the mixing container. Continue mixing for approximately two minutes.

Mixing ratio

Nanten Acrylic Hardener is used as the hardener, and the required amount depends on the working temperature.

1 dl of hardener = 64 g

+30°C 1 wt-%

+20°C 1.5 wt-%

+10°C 3 wt-%

+3°C 5 wt-%

Coverage

Approx. 0.3–0.5 kg/m², depending on the porosity and surface roughness of the acrylic mortar substrate. A minimum of >0.3 kg/m² per application must be used to ensure proper curing

Application instructions

Thoroughly mixed Nanten Acrylic Sealer 305 is poured onto the floor in a bead and applied using a short-nap roller or a rubber squeegee. Once the topcoat has dried, a second coat may be applied if necessary.

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Colour	Colorless
Package size	10 kg metal container and 180 kg drum
Storage	+5°C to +25°C, shelf life up to 6 months. Must be stored in a warm location in tightly sealed original containers.
Mixing time	Approx. two minutes
Density	1 kg/l, ISO 2811
Usage temperature	+3°C...+30°C
Usage time	Once poured onto the floor: approx. 10 minutes. Working time shortens as temperature increases.
Drying time	Recoat after approx. 60 minutes. Fully loadable after approx. 2 hours.
Adhesion strength	> 2.0 MPa
Viscosity	(+25°C): 40-60 mPas
Thinner	Do not dilute
Method of application	Applied with a brush or mohair roller
VOC content	< 0 g/l EU VOC 2004/42/EC (Cat A/j) max. 500 g/l (2010)

Remember to consult the Maintenance Instructions for Coated Floors and the product Safety Data Sheet on our website at www.fescon.fi, or request a copy by calling +358 9 274 7970. Although the technical details provided in this product description are based on our best knowledge and experience, the information above should always be regarded as indicative. The user is responsible for verifying the suitability of the product for the intended application. If the instructions are not followed, the user assumes full responsibility for any resulting damage or consequences. Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.