

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

SYLOTHIX 51

Product description

Fine polyethylene fibre for thixotropic thickening of coatings. Normally added 1–3 wt-% into component A of the coating and mixed thoroughly for 5–10 minutes before adding the hardener.

Applications

- Used for stiffening epoxy and acrylic coatings, e.g. in upturns

Instructions

Application instructions

- Normally added 1–3 wt-% into component A of the coating and mixed thoroughly for 5–10 minutes before adding the hardener.

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Type	Powder, fibrous
Colour	White
Package size	3 l (0.3 kg) tin can, 10 kg paper sack
Storage	Store in a dry place

Remember to consult the Maintenance Instructions for Coated Floors and the product Safety Data Sheet on our website at www.fescon.fi, or request a copy by calling +358 9 274 7970. Although the technical details provided in this product description are based on our best knowledge and experience, the information above should always be regarded as indicative. The user is responsible for verifying the suitability of the product for the intended application. If the instructions are not followed, the user assumes full responsibility for any resulting damage or consequences. Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.