Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

LIME-CEMENT PLASTER KS 50/50



Product description

Fescon Lime-cement plaster KS 50/50 is an air entrained, lime cement based dry mortar. The maximum grain size is 3.0 mm or 1.2 mm. Lime-cement plaster KS 50/50 is suitable to be used as adhesion, filling and surface mortar.

- Reliable long-lasting solution
- Extremely weather-resistant
- Breathable
- Excellent machinability
- Can be sprayed and applied manually

Applications

- Burnt brick and lime sand brick
- Lightweight gravel concrete and lightweight concrete
- Lime-cement plastering
- Traditional plastering (e.g. stick plastering)

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

Instructions

Base

The adhesive plaster (Fescon KS 10/90 or KS 35/65) must harden for at least one day before filling. If necessary, wet the base before applying the filler.

Mixing

Refer to the bag for how much water the plaster requires. Add the dry material to the water and mix with a concrete mixer for around ten minutes. With a power mixer or a drill paddle, around one to three minutes of mixing is sufficient. Let the plaster stand for around ten minutes and mix it again for a short while. Find the correct consistency at this stage by gradually adding the rest of the water. We do not recommend adding all of the water right at the start. Every batch must be mixed in the same way. The finished plaster remains workable for around two to three hours.

Work instructions

Apply the filling plaster with a plaster trowel or a pump. A suitable thickness for one layer of filler is around 15 mm. If the layer thickness exceeds 20 mm, the filler must be applied in several layers so that the previous layer has had time to dry for one to two days before the next layer is applied. In dry conditions, the base must be wetted before applying a new layer of plaster. Screed the filler plaster with a board. You can also carefully float the surface with a wooden tool to level the surface. Usage of dry plaster with a layer thickness of 15 mm

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

is approx. 30 kg/m^2. The lowest application temperature is +5°C and the recommended temperature is +10°C to +20°C. Plastering is not recommended in direct sunlight or in windy weather. Plastering nets mitigate the risk of cracking when mortar is drying. The net should be used especially at the connecting points of various materials, cracks in old brick walls, for reinforcing openings and corners, and plastering of various block surfaces (lightweight concrete, lightweight gravel, concrete). The correct position of the net in the plaster is 1/3 of the surface, however at least halfway outside.

After treatment

Filling plastering should be treated for at least three days with water irrigation. Aftercare should be started as early as possible to prevent plasticity cracks in the fresh mortar. In dry or windy conditions, aftercare should be started almost as soon as the mortar has sufficiently adhered to tolerate irrigation. If necessary, adhesive plastering should also be treated with water irrigation.

Other considerations

- For pumping render mortars and vertical joint concretes with a maximum aggregate size of 3 or 4 mm, it is recommended to use a sufficiently powerful rendering pump with a minimum power output of 5.5 kW and a stator size suitable for 7 or 8 mm aggregates. The use of automatic mixing pumps is not recommended, as the mixing time in automatic systems is too short. This may negatively affect the solubility of the mortar admixtures and the performance properties of the mortar.
- Lime-cement plaster in big bags is optimized for use with automatic silos. For small bags, we recommend a batch mixer or equivalent to ensure sufficient mixing power, an adequate maturation time of 10 minutes, and a short re-mixing before rendering.

Waste handling

Storage and handling of waste
See the separate storage and disposal instructions https://www.fescon.fi/en/material-bank

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Material usage	Approx. 30 kg/m^2 with a 15 mm layer thickness
Water requirement	4.0 - 5.0 l/25 kg
Finished compound	13-14 l/25 kg
Maximum grain size	1.2 mm or 3.0 mm
Package size	25 kg and 1000 kg
Storage	Storage time in a dry location approx. 1 year
Density	1.8 kg/dm^3
Workability time	2-3 h
Air content	Approx. 15%
Frost resistance	Flexural and compressive strength do not decrease after 200 melt-freeze cycles
Flow/plasticity	Hägermann 170 mm
Water retention capacity	80 - 90%
GWP A1-A3	0,26
GWP unit	kg CO2e/kg
Method for calculating the GWP value	Generic

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.