

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 28.3.2026 Printed 13.5.2026

BEDDING PLASTER LF RD



Product description

Fescon Bedding Plaster LF RD is a polymer-based low-dust bedding plaster for interior walls. Minimum delivery 3 pallets.

Applications

- Wall and ceiling surfaces in dry spaces
- Suitable for rock material bases and board surfaces
- The levelling compound cannot be used for floor levelling or as a base for tiling
- Low dust generation during mixing

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

Instructions

Mixing

Refer to the package for how much water the levelling compound requires. Add the dry material to the water and mix with a drill paddle for around one to two minutes. Let the levelling compound stand for at least fifteen minutes and mix it again for a short while. The finished levelling compound remains workable for around one day. The adhesion and wear resistance of the levelling compound can be improved by replacing 10% of the water with Fescon Primer.

Work instructions

The base should be solid, clean and free from any dust or other materials that could compromise adhesion. Before starting work, all structural components at risk of being damaged during levelling must be protected. Apply the levelling plaster on the surface (surface moisture must be below 90%) using either a plaster sprayer or steel trowel. Any excess plaster may be recovered and reused. If you apply several layers of plaster, allow the previous layer to fully harden before applying the next layer. Depending on the conditions, hardening takes one to two days. If necessary, the dried surface is sanded after each plaster application. The levelled surface can be treated with LRF or wallpapered or painted.

Other considerations

Do not leave the levelling compound in the pumps and hoses for longer than a day. Excess moisture of the structure may cause yellowing of the putty. Surfaces must be levelled in accordance with the general quality standards for indoor renovations (SisäRYL 2013).

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>



Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Updated 28.3.2026 Printed 13.5.2026

Technical information

Material usage	1 mm layer aprox. 1.2 kg/m ² (full levelling max. 1-3 mm/application)
Water requirement	4.8-5.6 l/20 kg
Type	Powder
Binder	Polymer adhesive
Aggregate	Limestone powder. Limestone powder contains small amounts of quartz, but the weight content of alveolar quartz is less than 1%, so the product is not classified as harmful in terms of quartz.
Colour	Whitish
Maximum grain size	0.6 mm
Package size	20 kg
Storage	Storage time in a dry location approx. 1 year
Layer thickness	1 - 5 mm
Lowest usage temperature	+10°C
Workability time	1 day
Coatability	Surface levelling, painting or wallpapering
Hardening time	Approx. 1 day at +20°C, approx. 2 days at +10°C Drying time depends on layer thickness and the humidity in the drying area
Adhesion strength	> 0.5 MPa (for a concrete surface)
Reaction to fire	A2
Exposure class	RL 01 - RL 03 (RL 04 with addition of primer)
Waterproofness	Not waterproof
Emission class	The M1 product meets the EU taxonomy criteria for formaldehyde emissions (< 0.06 mg/m ³) and carcinogen emissions (< 0.001 mg/m ³)

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.