

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

BOLTING PLASTER SR



Product description

Fescon Bolting plaster SR, is a pumpable special plaster for reinforcement work in rock construction. The binder is made of sulphate-resistant cement. Used in tunnel excavation, and rock and infrastructure construction. CE-marked, ready-to-use dry mix that meets quality and strength requirements.

- Ready-for-use dry mix product with strength classification
- Easy pumpability and good filling ability
- Remains in place in vertical holes
- Strength class C 40/50
- Exposure class XC4, XS3, XD3, XA3 (100 year service life)
- Bolting plaster SR fulfils the pull-out test requirement specified in standards EN 1504-6 and EN 1881

Minimum delivery quantity for big bags is 3 bags.



Applications

- Grouting of anchor bolts used in rock construction.
- Post-injection of expansion-shell anchor bolts (CT bolt or equivalent)

The product is listed in the portal for building products that can be used in Nordic Swan Ecolabelled buildings.

Instructions

Base

- The drill hole temperature is +5°C...+25°C.
- The drill hole has been flushed with pressurised water and, if necessary, blown with compressed air.
- The bold holes must be clean, solid and dust-free.

Priming

- The drill hole is not primed

Work instructions

- The work area must be completely protected from wind, sun and rain.
- During the bolting and while the plaster is hardening, the air and drill hole temperature must be +5°C...+25°C.
- A sack (25 kg) is mixed with 4.7–5.0 litres of cold water. If the product will be pumped, add 18–20% of water of the weight of the dry product. The bolting plaster has the correct amount of water when the it does not drain out of a vertical drill hole.
- The amount of water must be as instructed in the product card. Deviating from the recommended amount of water reduces the bolting plaster's strength properties, increases the bleeding risk, affects the bolting plaster's strength development, and weakens workability.

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

- Mix the bolting plaster carefully into a uniform paste (using a horizontal pan-mixer or continuous mixer).
- The bolting plaster is pumped into drill holes in the rock with a suitable plaster pump. The bolting plaster must fill the drill hole completely.
- The bolting plaster must be protected from mechanical disturbance during its strength development.
- Workable for about one hour after adding water.
- When finished working, wash tools immediately with water.
- Remove any dried bolting plaster mechanically.

Other considerations

- Work is performed according to the infraRYL instructions.

Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9
05800 HYVINKÄÄ
Tel. 020 789 5900
www.fescon.fi

Technical information

Material usage	Approx. 2.90 kg per running metre (approx. 1.60 l/m of prepared plaster) when using ø 25 mm corrugated bar bolts in 52 mm drill holes
Water requirement	4.7-5.0 l/25 kg
Type	Powder
Binder	Sulphate resistant cement
Colour	Grey
Maximum grain size	0.6 mm
Package size	25 kg, 800 kg
Storage	Storage time in a dry location approx. 1 year
Usage temperature	+5°C...+25°C
Workability time	Approx. 1 h
Strength class	C 40/50
Reaction to fire	A1
Exposure class	XC4, XS3, XD3, XA3 (100 year service life)
Chloride content	≤ 0,05 %

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.