

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

Updated 8.4.2026 Printed 15.5.2026

## SILICONE RESIN PRIMER MC

### Product description

The Silicone resin primer is a primer that guarantees good adhesion, more even absorption and better grip for concrete, board and plaster surfaces, and paint surfaces in a good condition.

- Regulates absorption
- Improves adhesion and grip
- Alkali-resistant
- Easy to work with
- White or tinted
- Thin with 5-20% water depending on the base



### Applications

- Concrete surfaces
- All plastered surfaces
- Board surfaces
- Firm old coatings
- For outdoor and indoor use

### Instructions

### Work instructions

Remove impurities from the surfaces, roughen and clean old coated surfaces, and entirely remove weak, old coatings. Do not work with the product in direct sunlight, in high winds, or when the air humidity is high (>80%). The fresh primer must be protected from too rapid drying, frost and rain during the work and until it has dried entirely. Apply the primer to a dry base using a brush, sprayer or a roller. Ensure that the base is durable, dry and clean. We recommend tinting the primer to match the coating. Thin with 5-20% water depending on the base. Thinning affects the opacity of the product's tint. Depending on air humidity and temperature, further treatment can be done no earlier than after 12 hours (+20°C/65% relative humidity).

### Cleaning of tools

Clean with water immediately after use.

### Waste handling

Storage and handling of waste

See the separate storage and disposal instructions <https://www.fescon.fi/en/material-bank>

Hämeenkatu 9  
05800 HYVINKÄÄ  
Tel. 020 789 5900  
www.fescon.fi

Updated 8.4.2026 Printed 15.5.2026

## Technical information

<b>Material usage</b>	Approx. 200 g/m <sup>2</sup> depending on the base
<b>Binder</b>	Plastic dispersion
<b>Tintability</b>	Can be tinted
<b>Package size</b>	15 kg
<b>Storage</b>	Store in a dry and cool storage. Do not allow to freeze. The maximum allowed storage temperature +25°C must not be exceeded. When the storage temperature is lower, the primer must be placed into an intermediate storage at a temperature of around +20°C before working.
<b>Density</b>	1.48 g/cm <sup>3</sup>
<b>Usage temperature</b>	The temperature of the base and air must be > +5°C
<b>Thinner</b>	Water
<b>VOC content</b>	EU limit value for the product cat. A/g 30 g/l (2010)

Limitation of liability, product use notes and restrictions: Please familiarize yourself with Fescon Oy's general terms of delivery and the design and work instructions related to the product.